


Aliphatic Polyisocyanates BAYHYDUR® Product Portfolio



Aliphatic Polyisocyanates Bayhydur Product Portfolio

	<u>NCO content</u>	<u>Functionality</u>	<u>Viscosity (23°C)</u>	<u>Solid content</u>
<i>Polyether modified, standard types</i>				
Bayhydur 3100	17.4 %	3.1	2,800 mPas	100 %
Bayhydur XP 2451/1	20.0 %	3.0	800 mPas	100 %
Bayhydur 401-70 **	9.4 %	2.9	600 mPas	70 % in MPA/X
<i>Polyether modified, 2nd. generation</i>				
Bayhydur 304	18.2 %	3.8	4,000 mPas	100 %
Bayhydur 305	16.2 %	4.0	6,500 mPas	100 %
Bayhydur XP 2700	10.6 %	4.0	80 mPas	65 % in DPGDME
<i>Ionically modified, 3rd. generation</i>				
Bayhydur XP 2487/1	20.6 %	3.4	5,400 mPas	100 %
Bayhydur XP 2547	22.5 %	3.0	650 mPas	100 %
Bayhydur XP 2655	21.2 %	3.2	3,500 mPas	100 %
Bayhydur XP 2759 **	11.0 %	3.1	6,500 mPas	70 % in MPA

** IPDI trimer